




High Purity SiC Powder



SiC Powder Characteristics

Characteristics	Unit	Spec.	
		ASEH1	ASEH2
Grain Size (D50)	mm	0.3	0.5
Particle size distribution	%	0.05~0.6mm ≥ 90	0.3~1mm ≥ 90
Typical Trace Elements			
B	ppm	< 1	
Na	ppm	< 1	
Mg	ppm	< 1	
Al	ppm	< 1	
P	ppm	< 1	
Fe	ppm	< 1	
Ca	ppm	< 1	
Co	ppm	< 1	
Cr	ppm	< 1	
Cu	ppm	< 1	
K	ppm	< 1	
Ni	ppm	< 1	
Ti	ppm	< 1	
W	ppm	< 1	
V	ppm	< 1	
Purity	%	> 99.9999	
Packing Density	g/cm ³	1.5	1

SiC Powder Particle Distribution



✉ material_sales@ostech.co.jp 🏠 <http://www.ostech.co.jp>

〒590-0023 大阪府堺市堺区南三国ヶ丘町2-2-74
TEL : 072-221-2778 FAX : 072-221-2779

2-2-74, Minami-mikunigaoka, Sakai-ku, Sakai, Osaka, JAPAN 590-0023
TEL : +81-72-221-2778 FAX : +81-72-221-2779